

AUTOFLEX AutoForm

Product Data Sheet

FIM techniques are used for cost effective manufacture of fascias, panels and casings in a variety of markets. MacDermid Autotype Limited films now offer advances in the durability of the film substrate, both in terms of chemical resistance and in terms of abrasion resistance.

PRODUCT DESCRIPTION

The product is a formable hard-coated polycarbonate film available in 180 - 480µm thickness. The coating is designed to allow shallow formability whilst retaining its abrasion resistant properties. The abrasion resistance of the product is comparable with conventional hardcoated polycarbonates.

Product Range

Finish / Thickness	180µm	250µm	380µm	480µm
Gloss finish	G180L G180 2L G180 HCL	G250L G250 2L	G380L	G480L G480 2L
Antiglare finish	A180	A250	A380	A480

Key: L = Laminated
 2L = 2 sides laminated
 HCL = Hard coat laminated

PRODUCT APPLICATIONS

The film is designed for in-mould decoration. The part is printed on the reverse, moulded to the shape required, and finally injection moulded on the reverse to give increased rigidity. The technique has applications in:

- White goods - Home appliance fascias
- Brown Goods - Electronics fascias
- Automotive - Heater controls
- Telecommunications - Mobile Telephones, Pagers

Major Benefits:

- Low hazard compared with spray coating.
- Easily formable by thermoforming or pressure forming.
- Provides a scratch resistant surface to the polycarbonate used as substrate.
- High gloss finish.



TYPICAL PROPERTY VALUES

CHEMICAL PROPERTIES

Property	Autoflex Autoform	Test Method
Chemical Resistance ¹	Resistant to: Alcohols Dilute Acids Dilute Alkalies Diesel Petrol Most Household cleaning agents Some aggressive organic solvents may leave small coating blisters	DIN 42 115

¹ See Test Method Manual

OPTICAL PROPERTIES

Property	Autoflex Autoform	Test Method
Gardner haze ¹ Gloss Antiglare	<0.3% 9% ± 2%	ASTM D1003-77
Gloss Level (60°) ¹ Gloss Antiglare	93% ± 5% 55% ± 5%	ASTM D2457-70
Total Luminous Transmission ¹	92% ± 2%	ASTM D1003-77
Yellowness Index ¹	<2	ASTM D1925-77

¹ See Test Method Manual.

Results based upon Gloss 250µm and Antiglare 480µm

MECHANICAL PROPERTIES

Property	Autoflex Autoform	Test Method
Elongation at break ¹	>100%	ASTM D882-83/ISO 527
Tensile strength at break ¹	≥61 N/mm ²	ASTM D882-83/ISO 527
Yield Strength ¹	60 N/mm ²	ASTM D882-83/ISO 527
Taber Abrasion ² Gloss Antiglare	<5% Not applicable	ASTM D1044-82 100 cycles 500g load, CS10F wheels
Pencil Hardness ²	HB	MacDermid Autotype Method
Flexibility	Passes 0.25" diameter mandrel	ASTM D522

¹ Values derived from polycarbonate manufacturer's data

² See Test Method Manual



GENERAL PROPERTIES

Property	Autoflex Autoform	Test Method
Relative Density ¹	1.2	ASTM D1505-85
Dimensional Stability ¹	<0.2% at 135°C MD Maximum Shrinkage	ASTM D1204
Humidity Testing ²	60 °C/95% RH for 1 week No visible change	MacDermid Autotype Method
Thermal Testing ²	4 weeks at 50°C No visible change	MacDermid Autotype Method
Thickness ¹	≤180µm ±10% 180 - 380µm ±7.5% >375µm ±5%	

Quoted figures are typical results based upon 250µ film

¹ Values derived from polycarbonate manufacturer's data

² See Test method manual

PROCESS OUTLINE**Printing/Decoration:**

Second surface decoration can be achieved with a variety of suitable screen printing inks.

Forming:

Thermoforming or pressure forming by the Niebling process should be carried out after decoration.

Cutting:

Trimming of the formed part.

Injection Molding:

The printed, formed and trimmed part is then inserted into a suitably designed injection mold tool cavity and resin injected onto the printed side of the film.

HAZARDS & WARNINGS

ENSURE ALL USERS READ THIS INFORMATION

This product is solely intended for use as an industrial film substrate for use in thermoforming and pressure forming applications. MacDermid Autotype Limited accepts no liability for use in any other way.

The main hazard associated with the film is the vapour produced when the film is exposed to heat prior to forming. Ensure that local exhaust extraction is in place to remove the vapour produced. See first aid instructions.

Ensure that light cotton gloves are worn throughout processing of the film.

FIRE PRECAUTIONS

Extinguisher Media: Use water, foam, PCF, CO₂

Exposure Hazards: Toxic fumes CO, CO₂, NO_x evolved during combustion.



SPILLAGE

N/A

FIRST AID

Inhalation of fumes during processing: Remove to fresh air. Give artificial respiration if necessary. Seek medical attention.

Ingestion & Eyes: N/A

Skin: Wash immediately with soap and water.

SHELF LIFE & STORAGE

This product should not deteriorate if stored in cool, dry conditions away from light and sources of UV, in the original sealed packaging. Use recommended within two years.

DISPOSAL

Can be treated as normal solid waste and disposed of via landfill or authorised incineration.

PACKAGING

Sheets 100 sheets per pack <380µm, 50 sheets per pack ≥380µm

Rolls Maximum width 122cm on a 6" core.

Revision 08/12/V1

The information and recommendations in this publication are believed to be accurate and are offered in good faith. Suggestions concerning uses and applications are only the opinion of MacDermid Autotype Limited and users should carry out their own testing procedures to confirm suitability for their purposes. Except in the case of death or personal injury caused by the materials, MacDermid Autotype Limited MAKES NO WARRANTY OF ANY KIND AND EXCLUDES ANY STATUTORY WARRANTY EXPRESS OR IMPLIED other than that materials conform to their current applicable standard specification. Statements herein therefore should not be construed as guarantees of satisfactory quality or fitness for purpose. The responsibility of MacDermid Autotype Limited for claims arising out of breach of guarantee, negligence, strict liability or otherwise is limited to the purchase price of the material. Suggestions concerning working practices and procedures are based on the practices adopted by existing users of the products and are made in good faith. IT IS THE RESPONSIBILITY OF THE USER TO ENSURE THAT ALL RELEVANT HEALTH AND SAFETY LAWS AND REGULATIONS ARE COMPLIED WITH. MacDermid Autotype Limited does not provide any advice on such laws and regulations and accepts no responsibility, express or implied, for breach of such regulations. WARNING: Nothing in this guide or in these technical specifications should be construed to imply or suggest that the user employ operations or create articles, which would infringe any patents belonging to third parties. Specifically, without limitation, using these products to form three dimensional printed or coloured products under certain conditions may infringe one or more of the following patents or their equivalent patents in other jurisdictions:

US 5,108,530

US 5,733,651

US 5,648,414

It is the customer's responsibility to ensure that its operations, the conditions of processing, and articles of manufacture do not infringe the foregoing patents, or any third party patents. MacDermid Autotype Ltd does not accept responsibility in this regard. With regard to the foregoing specifically noted patents, if a customer chooses to operate under the conditions claimed in the applicable patent in the applicable jurisdiction it is MacDermid Autotype Ltd understanding that licenses can be obtained from Bayer Aktiengesellschaft. However, obtaining such a license shall be the sole responsibility of the customer, as MacDermid Autotype Ltd assumes no responsibility for infringement of such patents.

© 2012 MacDermid Autotype Ltd

