

# AUTOTEX STEEL

## Product Data Sheet


Textured Hardcoat Polyester Film



### DESCRIPTION

**Autotex Steel** is a high quality textured hardcoat polyester\* film, for applications requiring a combination of high abrasion resistance and flexibility such as embossed membrane switches. **Autotex Steel** gives a stainless-steel look when printed with metallic ink and can also give an effective woodgrain appearance.

**Autotex Steel** is available in sheets and rolls. Note that in the roll format, the steel grain runs in the machine direction – that is, parallel to the length of the roll.



### PRODUCT RANGE


Products	Finish	Gauge	
		150µm	200µm
<b>Autotex</b> with 0-series ink primer for solvent based screen printing inks	Steel	S150	S200
<b>Autotex</b> with 7-series ink primer for UV screen printing inks and solvent based screen printing inks	Steel	S157	S207

### PRIMER

**Autotex Steel** has an ink adhesion primer on the second surface. Two versions are available:

The standard 0-series ink-receptive coating for solvent based screen printing inks. This primer has also been used successfully with some digital UV inkjet printers. Please contact MacDermid Autotype for more information.

The 7-series primer offers excellent adhesion to a wide range of solvent based screen printing inks and UV screen printing inks.



## MIRROR INKS

We have found that some mirror screen printing inks can be more brittle than graphic inks and, for this reason, we recommend that customers perform their own printing trials and in house evaluations. 0-series ink primer is particularly good for creating blemish free prints with mirror inks.

## WINDOWS

**Autotex Steel** can be screen printed with Windotex windowing lacquers to obtain a clear window. The cosmetic quality of the printed window can be affected by the steel finish, i.e. where there are deep lines in the texture these may be seen in a printed window. Special printing guidelines are available in the Windotex Processing and Safety Recommendations.

## TYPICAL PROPERTIES

Property	Typical Value	Test Method
Haze <sup>1</sup>	50% ±5%	ASTM D1003
Total luminous transmission <sup>1</sup>	92% ± 2%	ASTM D1003
Gloss level (60°) <sup>1</sup> with the grain (MD) against the grain (TD)	25-30 Gloss Units 8-10 Gloss Units	ASTM D2457 (Modified to test method 022)
Yellowness index <sup>3</sup>	<3	ASTM E313
Hardcoat adhesion <sup>3</sup>	Pass	Test method 080
Switch life <sup>1</sup>	>5 million actuations	Test method 003
Tensile strength at break <sup>2</sup>	172 N/mm <sup>2</sup>	ASTM D882
Breakdown voltage <sup>2</sup> 150 μ 200 μ	16 - 18 kV 18 – 20 kV	ASTM D149
Dimensional stability <sup>3</sup>	0.2% max. shrinkage MD at 120°C	Test method 094
Thickness all grades <sup>1</sup>	Nominal ± 10%	Test method 096
Maximum processing temperature	120°C	-
Maximum use temperature <sup>1</sup>	Low humidity (<10%RH) 85°C High humidity (10-95%RH) ≤60°C	Test method 012
Minimum use temperature <sup>1</sup>	-40°C (-40°F)	Test method 012
Chemical resistance	Excellent resistance to many common industrial solvents and household chemicals - please see <b>Autotex</b> Solvent Resistance Data Sheet	



<sup>1</sup> For details of test method, please contact MacDermid Autotype

<sup>2</sup> Data derived from base film manufacturer's literature. The coating slightly enhances most properties

<sup>3</sup> Specification value

\* The term polyester is the generic term for a number of different polymers, of which polyethylene terephthalate (PET) is the most common. PET is used in MacDermid Autotype High Performance Film Systems polyester film products

Note – Performance characteristics may be subject to change

## CONTACT INFORMATION

To confirm this is the most recent issue, please contact MacDermid Autotype

[www.macdermid.com/autotype](http://www.macdermid.com/autotype)

<p><b>North America</b> MacDermid Autotype Inc. 245 Freight Street Waterbury, CT 06702, USA (800) 323 0632 autotypeusinfo@macdermid.com</p>	<p><b>Europe</b> MacDermid Autotype Ltd. Grove Road, Wantage, Oxon OX12 7BZ, UK +44 (0) 1235 771111 salesupport@macdermidautotype.com</p>	<p><b>Asia</b> MacDermid Autotype Pte Ltd. 14, Joo Koon Crescent, Singapore, 629014 +65 643 00701 autotype-asia@macdermid.com</p>
---	---	---

The information and recommendations in this publication are believed to be accurate and are offered in good faith but do not constitute specifications. Suggestions concerning uses and applications are only the opinion of MacDermid Autotype Limited and users should carry out their own testing procedures to confirm suitability for their purposes. Except in the case of death or personal injury caused by the materials, MacDermid Autotype Limited MAKES NO WARRANTY OF ANY KIND AND EXCLUDES ANY STATUTORY WARRANTY EXPRESS OR IMPLIED other than that materials conform to their current applicable standard specification. Statements herein therefore should not be construed as guarantees of satisfactory quality or fitness for purpose. The responsibility of MacDermid Autotype Limited for claims arising out of breach of guarantee, negligence, strict liability or otherwise is limited to the purchase price of the material. Suggestions concerning working practices and procedures are based on the practices adopted by existing users of the products and are made in good faith. IT IS THE RESPONSIBILITY OF THE USER TO ENSURE THAT ALL RELEVANT HEALTH AND SAFETY LAWS AND REGULATIONS ARE COMPLIED WITH. MacDermid Autotype Limited does not provide any advice on such laws and regulations and accepts no responsibility, express or implied, for breach of such regulations. Statements concerning the use of products described herein should not be construed as recommending the infringement of any patent and no liability for infringement arising out of such use is assumed.