

SIGMAGRAF UVJET TM

Product Data Sheet

Textured Matt Hardcoated Polyester Film



DESCRIPTION

SIGMAGraF UVJet TM is a high performance, durable, hard coated polyester film with a textured matt finish. The film is designed for graphics applications where excellent flexibility, chemical resistance and abrasion resistance are required. Used in conjunction with Sigmagraf HTA adhesive, it can also be used successfully in floor graphics applications. It is supplied with a sub-surface primer for UV curing and Latex digital ink.

SIGMAGraF UVJet TM is available in rolls 123cm x 50m



TYPICAL APPLICATIONS

- Hoardings, signage and interiors.
- Floor graphics.
- Visually demanding and durable display graphics.
- In-store decoration and cladding.
- Retail graphics and POP displays.
- Industrial fascias, nameplates and design applications.
- Indoor signage in high-traffic areas.
- Exhibition and museum graphics and displays.
- Building and architectural graphics.
- Schools, hospitals and corporate display graphics.

SHELF LIFE

2 years when stored in original packaging, in a cool (18-25°C) dry place (40-60% relative humidity), away from direct sunlight / UV light source.



PRINT AND PROCESS GUIDELINES

Operation	Instruction	
Working instructions	Handle film at edge to avoid marking Do not stack or roll until image is completely cured/dry - UV curing inks can take between 12 - 48 hours to reach maximum cure thus maximum adhesion to the SIGMAGraF film. When using new media, run a print test to ensure optimum performance	
Printing	See SIGMAGraF insert for printing and cutting guidelines Sub surface print i.e. print on the underside Reverse/flip your image before printing	
Film winding	SIGMAGraF is wound print receptive side in therefore the hard coat side is on the outside of the roll.	
UV curing ink jet - ink laydown settings ¹	For lamination to another film substrate	100% ink laydown
	As a backlit film	300% ink laydown

¹ For guidance only - specific trials need to be undertaken to determine best settings for printer, ink and substrate combination

TYPICAL PROPERTIES

Property	Data	Test Method
Haze ¹	58% ±5%	ASTM D1003
Gloss level (60°) ¹	7 ± 1.5 Gloss Units	ASTM D2457 (modified to test method 022)
Total luminous transmission ¹	92% ±2%	ASTM D1003
Yellowness index ³	<3	ASTM E313
Dimensional stability ³	0.2% MD @ 120°C maximum shrinkage	Test method 094
Hardcoat Adhesion ³	Pass	Test method 080
Anti-Graffiti performance ¹	Pass	ASTM D-6578-00
Chemical resistance	Please refer to SIGMAGraF Solvent Resistance Data Sheet	

¹ For details of test method, please contact MacDermid Autotype

² Data derived from base film manufacturer's literature. The coating slightly enhances most properties

³ Specification value

Note: The term polyester is the generic term for a number of different polymers, of which polyethylene terephthalate (PET) is the most common. PET is used in MacDermid Autotype High Performance Film Systems polyester film products.



CONTACT INFORMATION

To confirm this is the most recent issue, please contact MacDermid Autotype
macdermid.com/autotype

North America	Europe	Asia
MacDermid Autotype Inc. 245 Freight Street Waterbury, CT 06702, USA (800) 323 0632 autotypeusinfo@macdermid.com	MacDermid Autotype Ltd. Grove Road, Wantage, Oxon OX12 7BZ, UK +44 (0) 1235 771111 salesupport@macdermidautotype.com	MacDermid Autotype Pte Ltd. 14 Joo Koon Crescent, Singapore, 629014 +65 643 00701 sginfo@autotype.com

The information and recommendations in this publication are believed to be accurate and are offered in good faith but do not constitute specifications. Suggestions concerning uses and applications are only the opinion of MacDermid Autotype Limited and users should carry out their own testing procedures to confirm suitability for their purposes. Except in the case of death or personal injury caused by the materials, MacDermid Autotype Limited MAKES NO WARRANTY OF ANY KIND AND EXCLUDES ANY STATUTORY WARRANTY EXPRESS OR IMPLIED other than that materials conform to their current applicable standard specification. Statements herein therefore should not be construed as guarantees of satisfactory quality or fitness for purpose. The responsibility of MacDermid Autotype Limited for claims arising out of breach of guarantee, negligence, strict liability or otherwise is limited to the purchase price of the material. Suggestions concerning working practices and procedures are based on the practices adopted by existing users of the products and are made in good faith. IT IS THE RESPONSIBILITY OF THE USER TO ENSURE THAT ALL RELEVANT HEALTH AND SAFETY LAWS AND REGULATIONS ARE COMPLIED WITH. MacDermid Autotype Limited does not provide any advice on such laws and regulations and accepts no responsibility, express or implied, for breach of such regulations. Statements concerning the use of products described herein should not be construed as recommending the infringement of any patent and no liability for infringement arising out of such use is assumed.